



## SBRT

### PRODUCT DESCRIPTION:

SBRT is a 400 mic, green PVC film coated with transparent, removable adhesive. Material was intentionally designed for sandblasting on stone. Product is dedicated for cutting plotters.

### PRODUCT STRUCTURE:

Film: 400 mic, monomeric, green PVC film

Adhesive: removable, transparent, water-based dispersion of polyacrylate

Liner: one-side siliconized, 121 gsm, "claycoated" type backing paper

### RANGE OF APPLICATION:

SBRT is dedicated for sandblasting on stone.

### PHYSICAL FEATURES:

	STANDARD NO.	VALUE
<b>Thickness</b>		
Thickness of PVC	ISO 2286-3	400 mic (±5%)
Total thickness (film+adhesive+liner)	ISO 2286-3	535 mic (±5%)
<b>Tensile stress at break</b>	ISO 527-3/2/200	min. 18 MPa [MD]
<b>Tensile strain at break</b>	ISO 527-3/2/200	min. 140 % [MD]
<b>Dimensional stability</b>	ASTM D 1204	-1 % [MD] ±1% [CD]
<b>Adhesive Power</b>		
Initial	FINAT 9	3.2 N/25 mm
After 20 min	FINAT 1	2.2 N/25 mm
After 24 h	FINAT 1	4.2 N/25 mm
<b>Temperature range</b>		
While applying	-	from 12oC to 40oC
While exploiting	-	from 10oC to 40oC
<b>Flammability</b>	Adhered to aluminium, glass or steel – self-extinguishing*	
<b>Durability</b>	90° vertical exposure	3 years (unprinted)
<b>Shelf Life</b>	2 years (in original packaging, at 20 oC and 50% relative humidity)	

\*\* Producer's internal test method



## DURABILITY

The data concerns vertical surface exposure of an unprinted/unprocessed film. The outdoor durability relates to the temperate climate of Middle Europe. If the film is exposed to extreme weather conditions, such as austere insolation, high UV radiation or humidity it may undergo accelerated deterioration. PVC film may also weaken in greatly contaminated areas and regions of high altitude.

## HANDLING & PROCESSING

Recommended storage conditions: 50% of relative humidity, 20 °C, in original packaging.

Customer should always store rolls together with label which consist information about type of product, dimensions of roll and batch number. Any claims or requests will not be accepted without information about batch number.

During storage time shrinking of the edges of monomeric PVC film could be noticed.

To obtain good print quality/good processing results we recommend acclimatize rolls in printing/processing room min. 24 hour before printing/processing. Large fluctuations in temperature and humidity between the room and the material have an impact on flatness and printability of material.

If printed, the ink must be perfectly dry before further processing e.g laminating or application. Features of products could be changed by the residuals solvents. The surface on which product is applied must be free of dust, grease, lubricant and any other substances which may hinder the film from adhesion.

Due to wide range of possible uses and applications customers should independently verify the appropriateness of material for their explicit purpose, prior to use. We strongly recommend customers conduct own tests before each application.

## IMPORTANT NOTICE

The information included in the present publication is based upon our knowledge as well as practical experience and can be changed without prior notice. All information always represents an average, a minimum or maximum value and should be considered as such.

This data is displayed only in order to serve as a source of information and is given without guarantee and does not constitute a warranty. All presented information refers to unprinted/unprocessed products. Features of products could change after printing/processing due to this reason all printed/processed products are not covered by warranty.

**ALPHASET**  
TECHNOLÓGIE A MATERIÁLY NA VÝROBU REKLAMY

ALPHASET spol. s r.o.  
Kopčianska 19, 851 01 Bratislava  
tel: +421 2 6381 2255  
mobil: +421 918 656 524  
e-mail: [alphaset@alphaset.sk](mailto:alphaset@alphaset.sk)

